

DATA SHEET

700D DENSICURE

DENSIFIER

DENSICURE POTASSIUM

DENSIFIER



DESCRIPTION

Densicure is a Potassium Densifier developed by All Purpose Coatings. It is designed to penetrate deep into concrete and react with the free calcium and lime, providing a harder, densified surface that will be more resistant to wear chemicals and dusting. Densicure reacts to create a calcium silicate hydrate that fills the voids in the concrete. This increases the strength and durability of the concrete and makes the surface less permeable, which can help prevent staining and the build-up of efflorescence. Densicure should be applied to fresh concrete cured for a minimum of seven days and should not be applied to any surface which has been painted or otherwise treated in a way that may impede penetration and affect the desired properties. Cleaning will be necessary in this situation to allow the Densicure to penetrate and react with the concrete.

PRODUCT INFORMATION

Shelf Life	2 years. Store in a cool, dry area and out of direct sunlight
Coverage	4-7m ² /L depending on the method of application and porosity of the surface
Return to Service	Light Foot Traffic: 1-3 hours after completion of the job. Vehicle Traffic: 24-48 hours after the completion of the job. Continuous Hardening: For a period of up to a month, the product will continue to harden

ENVIRONMENTAL CONDITIONS

Temperature and the surrounding atmospheric conditions will play a part in the curing process.

Industry standards recommend the accurate recording of times and dates, batch numbers, consumption rates, and environmental conditions including the substrate and air temperatures, humidity levels, and dew point readings during both the application and curing process. Full material warranties cannot be provided unless all the relevant data has been recorded accurately.

SURFACE PREPARATION

Concrete is to be clean and free of grease, oil, paint or any curing agent before application. Densicure should be applied to fresh concrete cured for a minimum of seven days and should not be applied to any surface which has been painted, coated or otherwise treated in a way which may impede penetration.

PRODUCT APPLICATION

Clean surface if required, allowing adequate time for it to dry completely. The treated surface should be dry, free of debris and absorbent.

Liberally apply Densicure by Spray or Flood Coat with a bristled broom and/or roller. Ensure the entire surface receives a "wet look" on application. Absorption of the product should take approximately one minute.


Leave the surface to soak for 20 minutes before reapplying a second coat of Densicure.

RECOMMENDED USES

- As a Concrete Sealer / Protectant
- To Densify Concrete for Diamond Polishing
- To Enhanced Gloss
- Harden and Increase the Lifespan of Concrete

FEATURES & BENEFITS

- Reduces Porosity and Permeability of Concrete
- Minimise the Occurrence of Efflorescence
- Reduces Small Moss, Mould and Algae Growth
- Retains a Natural Look
- Reduces Dust
- UV Stable
- Silane Free
- Water Based and No Odour
- Will not Flake, Peel or Scratch-off
- Suitable for Food Areas
- Non-flammable
- Chemical and solvent resistant

 Refer to individual SDS and Installation Instructions for system specifications and recommended PPE.

DATA SHEET
**700D DENSICURE
DENSIFIER**
DENSICURE POTASSIUM
DENSIFIER



CAUTIONS

- Do not apply below 0 Centigrade and above 40 centigrade.
- The surface cannot have existing non-permeable coatings.
- Concrete must be dry.
- Do not allow puddling/pooling on the surface during application. A white residue could form. While this will not affect the performance and will dissipate over time with cleaning, it is not a desirable outcome and should be avoided where possible.
- Spills, including water should be cleaned up as soon as possible.

PHYSICAL PROPERTIES

- Alkali Resistant
- Acid Resistant
- Chemical Resistant
- Solvent Resistant
- Silane Free
- UV Resistant

In an emergency, contact the Poisons Information Centre on 13 11 26 or a doctor for advice.

IF THE SITUATION IS LIFE THREATENING, DIAL 000 IMMEDIATELY.

DISCLAIMER: Please ensure you read the SDS & TDS thoroughly & carefully before the use or application of any All Purpose Coatings product. These documents contain information in context to how you will apply the product, including if it is being used in conjunction with any other products or systems, and to what surface the product will be applied. All-Purpose Coatings Pty Ltd does not accept any liability either directly or indirectly for any losses that arise from the use or application of the product in accordance with any advice, specification & recommendation given by the companies' documentation or representatives at any point in time. Application, performance & safety data may change from time to time. It is the user and/or applicators' responsibility to ensure they have the latest copy of any documentation pertaining to their project.

Industry standards recommend the accurate recording of times and dates, batch numbers, consumption rates and environmental conditions including substrate and air temperatures, humidity levels and dew point readings during both the application and curing processes. Full material warranties cannot be provided unless all the relevant data has been recorded accurately.



Refer to individual SDS and Installation Instructions for system specifications and recommended PPE.