

# DATA SHEET EPO100G GLAZE EPOXY

100% SOLIDS, LOW VOC,  
CLEAR RESIN



ALL PURPOSE COATINGS

## DESCRIPTION

EPO100G® Glaze Epoxy is a two-component cycloaliphatic amine cured resin with a 100% solids content. Developed and produced by All Purpose Coatings, it serves as a floor and wall solution that can be easily rolled on. Once applied, EPO100G® exhibits a self-leveling, high gloss finish that is water-clear. Its formula is suitable for use in various settings, ranging from industrial to residential applications, and it can offer long-lasting results with outstanding resistance to chemicals and vapors.

## PRODUCT INFORMATION

<b>Pot Life</b>	30-45 minutes at 25°C.
<b>Shelf Life</b>	2 years. Store in a cool, dry area and out of direct sunlight
<b>Mixing</b>	(2:1) 2 Parts EPO100G (Part A): 1 Part EPO100G (Part B)
<b>Coverage</b>	4-6m <sup>2</sup> /L Depending on the method of application and porosity of the surface and 1m <sup>2</sup> /L on a Metallic system to achieve a Diamond Finish.
<b>Heat Resistance</b>	Epoxy will not begin to soften until 90°C.
<b>Clean Up</b>	Clean tools with 150T Epoxy Thinners while still wet and discard rollers and brushes.
<b>Return to Service</b>	<b>Light Foot Traffic:</b> 24 hours after completion of the job. <b>Vehicle Traffic:</b> 24-48 hours after the completion of the job. <b>Sure Hardness:</b> 72 hours after the completion of the job. <b>Full Chemical Cure:</b> 7 days after the completion of the job.
<b>Recoat Time</b>	12-24 hours depending on the temperature.
<b>Work time per pack</b>	1-2 hours
<b>Tack free time</b>	8 hours at 25°C
<b>Maintenance</b>	Refer to APC Clean and Care guide.

## RECOMMENDED USES

- Mechanical workshops
- Factories and manufacturing Facilities
- Warehouses
- Loading bays and ramps
- Car parks
- Food processing plants
- Chemical and pharmaceutical Industries
- Laboratories
- Exhibition halls and showrooms.
- Washrooms and cloakrooms
- Wet and dry processing areas
- Government and education facilities
- Residential properties

## FEATURES & BENEFITS


- Australian Made
- High Gloss
- Excellent Adhesion
- Self-Levelling
- Self Priming
- Low VOC's (Volatile Organic Compounds)
- Low Viscosity
- Excellent Abrasion Resistance
- Excellent Chemical Resistance
- High Durability
- Water Clear
- Solvent Free
- Waterproof
- APAS Approved (Australian Paint Approval Scheme)

## ENVIRONMENTAL CONDITIONS

Temperature and the surrounding atmospheric conditions will play a part in the curing process of all epoxy products. Under conditions of low temperatures and high humidity, the final cured surface finish can be adversely affected potentially resulting in poor gloss retention, discolouration over time, poor overcoat ability, and inter-coat adhesion. Quite often these conditions will result in the formation of a white film over the surface often evident after contact with water. This chemical reaction with the atmosphere is commonly referred to as "amine bloom" or "amine blush".

If this occurs then the existing coating will need to be abraded to completely remove the affected surface to ensure the adhesion of subsequent application. In some cases, partial or complete re-priming may be necessary. Attention also needs to be paid to the substrate temperature which should be at least 10°C and preferably 5°C above the dew point during the curing phase. Ideal humidity is 50-70%.

Industry standards recommend the accurate recording of times and dates, batch numbers, consumption rates, and environmental conditions including the substrate and air temperatures, humidity levels, and dew point readings during both the application and curing process. Full material warranties cannot be provided unless all the relevant data has been recorded accurately.

 Refer to individual SDS and Installation Instructions for system specifications and recommended PPE.

# DATA SHEET

# EPO100G GLAZE

# EPOXY

100% SOLIDS, LOW VOC,  
CLEAR RESIN



## SURFACE PREPARATION

- Ensure the concrete is sufficiently cured to the recommended minimum of 28 days from completion.
- Diamond grind or Polyvac the substrate. The surfaces must be clean, dry, and free from all traces of loose material, old coatings, curing compounds, release agents, laitance, oil, and grease, etc. This must be completed by diamond grinding or a suitable cleaning method.
- To check that all traces of oil and other contaminants have been completely removed, sprinkle a few drops of water over the surface. If all water is quickly absorbed, the surface is sufficiently oil and grease-free.
- If water forms into globules that remain on the surface, further thorough treatment of the substrate is necessary.
- Substrate compression strength should be at least 25MPa, cohesive bond strength at least 1.5MPa, and moisture content below 4%.
- Repair and fill cracks with EPO100EP Epoxy Putty or Concrete Repair Kit.

## PRODUCT APPLICATION

Mix EPO100G® Epoxy Resin Part A thoroughly prior to combining with EPO100G® Epoxy Hardener Part B.

Mix 2 Parts A with 1 Part B (2:1) by volume. Mix with a drill mixer at a slow speed for 2 minutes. Ensure the sides and bottom of the container/bucket are mixed. Tilt the drill to the side to ensure the product on top of the container/bucket is mixing in with the product on the bottom. In normal curing conditions, the EPO100G® Coating Kit does not require an induction time and coating can begin immediately after mixing. For colder climates, see product cautions for further information on mixing and induction times.


For system-specific instructions, consult the All Purpose Coatings **Installation Instruction** documentation, located on the website. It is recommended that the first coat of EPO100G® be applied with a recommended 10% of Epoxy Thinners to ensure high penetration and adhesion to the coating substrate. Subsequent coats can be thinned but, a sufficient curing time will be required to allow the solvent content to evaporate from the product before re-coating or top coating when used as part of an All Purpose Coatings system. The re-coat time is typically, 12-24 hours at 25°C. Apply using a brush or lint-free roller.

If recoating after 72 hours a light sand will be required to ensure adhesion of any following coats.

**Without exceeding 4mm, apply thicker coats using a squeegee or notched trowel and let the product self-level.**

## CAUTIONS

- When used as a self-leveling floor coating, EPO100G® will not profile irregular substrates. For the profiling of defects on horizontal surfaces a suitable patching or repair mortar will be required.
- The mix ratio is calculated by product volume. **NOT BY PRODUCT WEIGHT.** Mixing product by weight may result in an unsatisfactory cure time or failure of the mix to cure entirely.
- To achieve optimum results in colder climates, you may need to warm the resin or introduce an induction time before application. This will jump start the curing process. For further information, consult All Purpose Coatings, technical advisers.
- Exposure to sunlight and UV radiation can result in discolouration and chalking of the cured surface. While this will have no adverse effect on the protective functions of the coating, the system can be finished with a UV stable and protectant top coat such as 500T Tetrathane®, Sparta60, or Sparta Guard.
- **EPO100G® Glaze is not suitable for deep pours or depths over 4mm due to loss of clarity. Refer to EPO100C® Clear, EPO100SCC Slow Cure Clear.**
- Spills, including water should be cleaned up as soon as possible.

 Refer to individual SDS and Installation Instructions for system specifications and recommended PPE.



# DATA SHEET EPO100G GLAZE EPOXY

100% SOLIDS, LOW VOC,  
CLEAR RESIN



## PHYSICAL PROPERTIES

<b>Solids content</b>	100 %	<b>Heat Distortion Temperature</b>	ASTM D648:50°C
<b>Finish</b>	Clear, Gloss	<b>Bond Strength to Concrete</b>	100% Concrete Failure
<b>Impact Strength</b>	High	<b>Resistance to Chemical Spills (7 days at 25°C)</b>	
<b>Compressive Strength</b>	ASTM D695:12,000 psi	Ammonia Solution (20%)	Sodium Hydroxide (30%)
<b>Tensile Strength</b>	ASTM D638: 3,900 psi	Sulphuric Acid (30%)	Kerosene
<b>Elongation at Break</b>	ASTM D638: 7.00%	Lactic Acid (5%)	Aviation Fuels
<b>Taber Abrasion Resistance</b> (mg or loss/1000 cycles) CS-17-wheel, 1 kg load	ASTM D4060: <0.1g loss	Sodium Chloride (50%)	Petrol
<b>Water Absorption</b>	ASTM D570:0/07% (2 hour boil)	Tannic Acid	Hydrochloric Acid (20%)
<b>Flexural Strength</b>	ASTM D790:7,800 psi	Acetic Acid (5%)	Toluene
<b>Shore D Hardness</b>	ASTM D2240:89		

Sample Identification	Critical Heat Flux (kW/m2)			Smoke Value %.min		
	≤11	≤11	≤11	5	1	2
Epoxy Coating Kit Tinted EPO100T®	Average: ≤11			Average: 3		
Epoxy Resin Clear Glaze EPO100G®	Average: ≤11			Average: <4		
Epoxy Resin Clear EPO100C®	Average: ≤11			Average: <4		

In an emergency, contact the Poisons Information Centre on 13 11 26 or a doctor for advice.

**IF THE SITUATION IS LIFE THREATENING, DIAL 000 IMMEDIATELY.**

DISCLAIMER: Please ensure you read the SDS & TDS thoroughly & carefully before the use or application of any All Purpose Coatings product. These documents contain information in context to how you will apply the product, including if it is being used in conjunction with any other products or systems, and to what surface the product will be applied. All-Purpose Coatings Pty Ltd does not accept any liability either directly or indirectly for any losses that arise from the use or application of the product in accordance with any advice, specification & recommendation given by the companies' documentation or representatives at any point in time. Application, performance & safety data may change from time to time. It is the user and/or applicators' responsibility to ensure they have the latest copy of any documentation pertaining to their project.

Industry standards recommend the accurate recording of times and dates, batch numbers, consumption rates and environmental conditions including substrate and air temperatures, humidity levels and dew point readings during both the application and curing processes. Full material warranties cannot be provided unless all the relevant data has been recorded accurately.

Refer to individual SDS and Installation Instructions for system specifications and recommended PPE.