

Independent Slip Testing Services

+61 (0) 411 600 733 www.sliptesting.com.au

🥍 +64 (0) 279 735 266 www.sliptesting.co.nz

Reduce Your Risk!*


Independent Slip Testing Services

AUSTRALIA | NEW ZEALAND | GLOBAL

Report Prepared for: All Purpose Coatings
Property Tested: 16 Hawkins Crescent, Bundamba

Client Address: 16 Hawkins Crescent, Bundamba QLD 4304 Australia Date of Test: 18-06-2024 Program #: 4004 Page: 13 of 17

Test Location	Surface Type	Surface Coating	Surface Conditions	Slider Conditioning	British Pendulum Number (BPN)	Slip Resistance Value & Slope Correction Value	TEST RESULTS (Slider96)	
Test Area 12.	epoxy flake	Mist S	environment: internal (dry area)	P400	55	(SRV)	Mean BPN result after	Classification
Ultra Flake Small- Grip 25 Finish		Neutral Grey	slope: <1.5 degrees	83	54	55	adjustments	Classification
		coating	surface: rough		57			
			test direction: anticipated pedestrian travel	lapping	56	(SCV)	55	P5
			other observations: n/a	64	55	n/a		



COMMENTS:

Temp: 24 deg.C

Weather: Internal- Non Air conditioned
Surface Cleaning: Tested as found

Testing Instrument W12- Serial #: WM007

Testing Technician: C.Rezuk

^ An individual result both below the result classification and below the mean result minus 20% shall be considered of lower classification

Reported Uncertainty for testing device: 3.0 BPN

ISTS GLOBAL HEADQUARTERS:

124 Hindes Street Lota QLD 4179 Australia

DISCLAIMER: ISTS accepts no civil liability or responsibility for any actions whatsoever that may arise as a result of the tests and the publication and issue of this test report. The test report is intended for viewing purposes solely for the named recipient identified above. The slip test report remains the property of ISTS. This report contains privileged and confidential information. The unauthorised reproduction of this report is prohibited.

Accredited for compliance with ISO/IEC 17025 testing and calibration. NATA is a signatory to the APLAC mutual recognition arrangement for the mutual recognition of the equivalence of testing, calibration and inspection reports.





Testing was carried out using the Wet Pendulum Test method using Slider 96 (4S rubber) in accordance with Australian Standard AS 4586-2013 Appendix A.